ECDA Indirect Inspection Tools - ACVG, Current Attenuation and DCVG

By Jim Walton

JW’s Corrosion Services, LLC

Indirect Inspection

ECDA is a four step process consisting of:

1. **Pre-Assessment**
2. **Indirect Inspection**
3. **Direct Examination**
4. **Post Assessment**

Indirect Inspection

- Keep it simple and well organized
- Use familiar test methods and available equipment
- Accept that it is time consuming
- Don’t cheat on the footage
- Review and evaluate daily
- Work safely

Tool Selection
AUCSC Field Workshop

- **Current Attenuation**
- **Close Interval Survey**
- **Alternating Current Voltage Gradient**
- **Direct Current Voltage Gradient**
- **Other**

ACVG

Alternating Current Voltage Gradient

ACVG

<u>NACE definition</u>

"A method of measuring the change in leakage current in the soil along and around a pipeline to locate coating holidays and characterize corrosion activity."

ACVG

- **Locate pipeline**
- **Locate coating defects**
- **Locate galvanic anodes**
- **Locate foreign structures (X or //)**
- **Location of bonds**

VOLTAGE GRADIENT

Current flowing through a RESISTOR will produce a voltage drop.

$$V = I \times R$$

… also called ??

VOLTAGE GRADIENT

Gradient =ΔV/Δd

ACVG - Current Flow

ACVG Hardware

1. ACVG Transmitter
   - Generates a signal for performing pipeline survey.

2. ACVG Receiver
   - Processes ACVG signal and displays results.
   - Optional data logger and/or GPS.

ACVG Hardware

- Transmitter (Tx)
  - Generates three frequencies:
    1. Locate frequency
    2. 4 Hz for fault finding
    3. 8 Hz for direction to fault
- Receiver (Rx)
  - Locate pipeline
  - Attachment for ACVG readings
    - Use 4 Hz de measure μV
    - Use 4 + 8 Hz to determine fault direction (phase shift)

Tx - Connections

- Rectifier
- Test Station
- Metering & Regulating

Transmitter

- **Current from the transmitter creates a voltage gradient around coating defects.**
- **Current density greatest at interface between the defect and the surrounding environment.**
- **Current density funtion of soil resistivity & Tx output.**

ACVG – Receiver Readings

- **An increase in voltage gradient will cause an increase in current density near a given coating defect on the pipeline under test**
- **Signal Current and Voltage effects viewed on instrument's display**
- **Signal Current direction is displayed as an arrow**
- **Voltage is identified as decibels (dB)**

ACVG – Shape of Readings

Rx – Direction to Fault

Rx – Direction to Fault

Fault Magnitude – dB **(decibel)**

- A decibel is a logarithm of a ratio, multiplied by a constant, or number, usually ***10*** or ***20***.

- If the ratio you are comparing is that of two voltage gradients, then $dB = 20 \log (\Delta V_2 / \Delta V_1)$

- Reference Voltage is $\Delta V_1 = 1\ \mu V$

- Every time you double or half your ***voltage***, the level change is ***+/-6 dB***

Current Measurement & Decibel levels

600 mA @ 40V

300 mA @ 20V

Position one pin over center of pipe and suspect defect. Complete clock direction to validate suspect location

Voltage Gradients

4 Hz Signal Voltage Gradient

Shape of ACVG response over coating defect

Directional Display

Front of receiver

GREEN

RED

Pipeline

3’
3’
3’

Make sure probes are in
good contact with
electrolyte

NEW YORK PLAINVIEW
UNITED METHODIST CHURCH
뉴욕감리교회
Probe contact in sidewalk seam

ACVG Rx Readings

Pipe 2’ to 3’ off curb and under macadam road surface

Using guard rail as remote
ground for transmitting
signal

Connection to structure at
grade level test box using #8 cu
stranded wire connected to pipe
below grade

Output OK
Over Temperature
Power Limit
Voltage Limit
Output Voltage Level
Output Level
Frequency Select
AC Supply

Pipe location below grade

ACVG

Pre-measured
distance for ACVG
data collection

Push the A-Frame spikes into the ground to take a reading.
No Rx adjustments.

ELF LF 8k CPS
Review
On/Off
Peak/Null
Depth
Current

Make good electrical contact on ground.

Moisten roadway to ensure good surface contact. Over many paved surfaces, wetting down the road will allow for sufficient ACVG measurements.

Typical display indicating possible coating defect (holiday)

E
D
C
Coating defects observed after excavation of pipeline

Section of coating removed
from pipeline after
excavation

Damage observed
after coating
removed

Data logging w/GPS

Interpreting Results

- No direct correlation between dB and size of fault
- dB indicates severity of current loss
- Factors affecting dB readings
  1. Tx output
  2. Current available at fault
  3. Quality of contact to ground:
     - Concrete
     - Sand
     - Railroad ballast
  4. Conductivity of path fault-to-ground (electrolyte, rain)

Interpreting Results

- Normally Faults are CATEGORIZED
  1. Manufacturer's recommendations
  2. Own internal documentation
  3. Recommended industry best practices

- Note that Transmitter output will affect dB readings because of the amount of current at the holiday. Apply correction to normalize the readings are utilized.

Interpreting Results

- Example:

  1. Severe – 80-100 dB
  2. Moderate – 65-80 dB
  3. Minor – 50 - 65 dB
  4. Note – 0-50 dB

Interpreting Results

- Can use 1A or othe current amount as a “standard” output, and refer all readings to it.

- Conversion

100 mA	+20 dB
300 mA	+10 dB
600 mA	+ 4 dB
1 A	no correction
2 A	- 6 dB
3 A	-10 dB

What can ACVG data tell us?

- It is a micro tool that pinpoints coating defects and can find:
  - Large coating defects
  - Small Coating defects
  - Severity of the coating defect
  - Possible interference areas
  - Shorted casings
  - CP cable breaks
  - Position of Anodes

ACVG tools

ELF LF 8k CPS
73
Review
On/Off
Peak/Null
Depth
Current
Mode
Shift
JUN 24 2003

ACVG with Current Attenuation

ACVG data

20in PCM and ACVG 03302006 AM 134
dB microvolt re
4 Hz current
100
90
80
70
60
50
40
30
20
10
0
0.3
0.25
0.2
0.15
0.1
0.05
0
633
635
639
642
645
647
649
656
660
664
668
671
674
679
682
685
687
691
695
699
Flags (every 50 ft)
ACVG indication
Current

External Corrosion Direct Assessment:

Four step process consisting of:

1. Pre-assessment
2. Indirect Inspection
3. Direct Examination
4. Post assessment

Indirect Inspection

One of these tool choices can be requires the use of two complementary tools

ACVG

AC Current Attenuation

Introduction to Basic Concepts

Need to understand behavior of AC current on a pipeline.

AC Current Attenuation

Pipe and Cable locators do not find pipelines (or header cables.....)

AC Current Attenuation

....they find magnetic fields.

AC Current Attenuation

WHY DOES IT MATTER ?

Distortion

AC-Current Attenuation

- [x] Passive
- [ ] Active

AC Current Attenuation

AC Current Attenuation

- Fast
- Easy
- Does not identify

AC Current Attenuation

☐ Passive

☑ Active

AC Current Attenuation

AC Current Attenuation

Applying a Signal

Connection
"Clip"

Signal Clamp
"Clamp"

Induction "Spill"

AC Current Attenuation

Ground stake too close to target conductor:
Less range, some signal transfer.

AC Current Attenuation

Bad ground choice causes more bleed off.
Place ground rod away from known adjacent pipes/utilities which may act as return paths.

AC Current Attenuation

Remote ground = better range, less signal transfer.
GENERAL RULE: position ground point at right angles to pipe.

AC Current Attenuation

Grounding to a structure which is also grounded can produce multiple signals.

AC Current Attenuation

AC Current Attenuation

Distortion

AC Current Attenuation

Distortion

AC Attenuation

- Theory

All AC Attenuation devices use the same basic principles. They send an AC signal on a metallic structure that causes a magnetic field to be propagated. This field is generated because of the alternating nature of AC current. Once the field has been established, a receiver consisting of multiple antennas and a magnetometer measures the field. Because the distance from the field is important, the depth of the pipeline needs to be established. This can be done using different frequencies of AC and integrating the depth data with the elctro-magnetic data.

AC Attenuation

- Theory (continued)

More sophisticated machines can also integrate the location and thus give a change over distance reading. For the machines that do not perform this function, plotting the readings or using a recorder can yield the delta signal loss over the distance traveled.

AC Attenuation

- Theory (continued)

All pipelines will loose the AC signal, pipelines with poor coating or large holidays will loose the signal at a greater rate. This rate can be correlated to the coating condition.

AC Attenuation

- Peak

  This is a typical peak signal response over a buried conductor. Peak response provides position and direction.

  Note that the maximum signal response occurs directly over the center of the underground conductor.

AC Attenuation

- Null

  In Null, minimum signal is encountered exactly over the center of the buried conductor field.

  A maximum signal response will be detected on each side of the minimum. If both of the "shoulders" are symmetrical, the Null point is accurate.

AC Attenuation

- Peak coil response is less sharp, but actually more accurate.

- Null antenna gives a sharp response which gives the impression of good accuracy, but can be less accurate than Peak.

AC Attenuation

Errors

1. Readings taken near the transmitter can be in error because the signals can circle around.
2. Reading taken at a pipeline location where the depth measurements can not be accurately or consistently obtained.
3. Readings at locations that have elbows, tees, abrupt changes in direction cause the magnetic flux to interact.

AC Current Attenuation

AC Current Attenuation

AC Current Attenuation

Peak response will
<u>ALWAYS</u>
be more accurate.

AC Attenuation Transmitter

Current Attenuation Tools

581
On/Off
Peak/Null
Depth
Current
Mode
Shift
6. 1. 2000

Current Attenuation Continued

What can CA data tell us?

- It is a macro tool that highlights the bigger problems in a coated pipeline system including:
  - Shorts to other structures
  - Grounding to electric neutral
  - Bad insulators
  - Large coating defects
  - Shorted casings
  - Other current distribution problems
  - Depth of cover at the same time (possible TPI)

  Any or all may affect the ability of the other tools to perform in a consistent and reliable manner.

Things to remember when conducting Current Attenuation Surveys

1) Always direct connect
2) Always use an independent ground
    a) Anode Bed b) Ground Stake c) Across an insulator?
3) Always have a map of the facility
4) Never use another utility as the ground return.
5) Never assume anything.
6) Shorts
    a) First signal loss may not be the short.
    b) There may be more than one short.
    c) There may be an unknown source.
7) Coating defects
    a) Take readings at the same intervals.
    b) Make sure unit and boot are perpendicular to the pipe.
    c) Hold unit steady and upright when reading current.
8) You do not always have to connect closest to the suspected short or coating defect.
9) More is not always better.

FACTS TO REMEMBER

1) Lower frequencies couple less.
2) Locators with a digital depth readout, current measurement and current direction provide more information and lead to more answers.
3) Verify with peak and null locates.
4) Log readings manually or digitally.
5) Take readings at every split or at equal distance.

Current Measurement
and
Current Direction

1) Current measurement is depth compensated.
2) If depth readings are erroneous, so is current.
3) PCM uses 98Hz for depth & 4 Hz for current.
4) PCM Current Direction is displayed in relation to Cathodic Protection current (from the anode to the pipe and back to the rectifier).
5) CD gives us the final determination many times before we dig a short. CD normally does not help in determining coating defects alone.
6) Electromagnetic receivers can obtain readings over various soil conditions including asphalt, concrete and water and still will obtain accurate readings.
7) Unit does not have to touch the ground but must be steady.

Other Applications with Current Attenuation

1) Looking for hot spots.

2) Determining the best location for a permanent ground bed.

3) Determining the effectiveness and life of a ground bed.

4) Pinpointing coating damage with an A-frame.

5) Yearly analysis of coating conditions.

Methodology using PCM for Current Surveys

- Use an independent ground and try to mimic your CP circuit when possible
- Make sure rectifiers are not influencing the signal (turn off AND disconnect if necessary)
- Isolate your circuit whenever possible (disconnect bonds for better surveys)
- Take readings at equal distances and record your distances
- Every 50 feet is a good standard(others can be used dependant on location)
- Use it as a macro tool and depth of cover tool (use A-frame for micro)
- Look for anomalies with more than a 5% change normally
- Make sure unit is upright and perpendicular to the pipe
- Stay on peak and check peak and null readings and verify depth when readings are suspect.
- Take multiple readings in one location if you are suspect of the accuracy.
- Know what is in the area of your pipe and what it is connected to it

Graphed data

CA Data

Current
Amps
2.5
2
1.5
1
0.5
0
0 200 400 600 800 1000 1200 1400 1600 1800 2000 2200 2400 2600 2800 3000 3200 3400 3600 3800 4000 4200 4400 4600 4800 5000 5200 5400
Footage (x5)
Current

AC Attenuation

The line marked 'A' to 'E' is the data collected, whilst the line '1' to '4' is the interpreted data.

At position 'A' the current falls and then returns to almost it's original level. This is probably due to field distortion of the locate signal and should be ignored or further investigation undertaken.

Steps 'B' to 'E' show definite steps (with some field distortion at the point of fault) and loss of signal. The recovered reading is less than the signal before the trouble.

AC Attenuation

Interpretation of Readings and Graphs

Pipe coating in good condition is shown as very little loss of current.

Pipe coating in poor condition is shown as a rapid loss of in current.

Mixture of good and poor coating which is shown as greater current loss over the section of pipe with poor coating.

AC Attenuation

The effect of a short or contact with another service is a sudden current loss.

The effect of a poorly coated steel shield in contact with the pipeline is to show reduced current in one measurement section.

This effect is either a section of perfect coating or ground conditions that are shielding the signal – dry or rocky ground.

AC Attenuation

AC Attenuation

Current Attenuation Survey Indicating Coating Defects - TRAINING DATA

PCM Transmitter set at west end of pipe segment. 4 Hz signal direction returning to transmitter.
Transmitter set at 300 ma < 20 volts

Current Attenuation Survey Indicating Coating Defects - TRAINING DATA

PCM Transmitter set at east end of pipe segment. 4 Hz signal direction back to transmitter.

Transmitter set at 2 amps < 20 volts

AC Attenuation
Holiday Locations
mA dc
250
200
150
100
50
0
0
50
100
150
200
250
300
350
400
450
500
Feet
AC Atten Trans @ 0
AC Atten x 10 Trans @1000

DCVG

Direct Current Voltage Gradient

Principles of DCVG

DCVG uses the differences between two reference electrodes. These differences can assist in pinpointing holidays and corrosion cells on a pipeline. DCVG, because it uses DC current, can also determine if the holiday is cathodic (protected) or anodic (corroding).

- Asynchronous interruption (0.3sec on, 0.7sec off) is required
- Accurately (± 4″) locates coating anomalies
- Differentiate between isolated (discrete) and continuous anomalies
- Predict relative importance/severity of anomaly
- Examine the direction of the current flow (anodic vs. cathodic)

What can DCVG data tell us?

- It is a micro tool that pinpoints coating defects and in some instances can give us a relative state of the cathodic protection at that indication and can find:
  - Large coating defects
  - Small Coating defects
  - Severity of the coating defect
  - Possible interference areas
  - Shorted casings
  - CP cable breaks
  - Position of Anodes
  - Cathodic/Anodic condition at the time

DCVG tools

G1

PCS-2000

DCVG meter

Similarities to ACVG

- Both require sufficient ground contact.
- Both require sufficient current flow on the pipeline to provide sufficient voltage gradient fields at holidays.
- Both can accurately detect and pinpoint positions of holidays, shorts, anodes, cable breaks and other areas of metal to dirt contact.
- Both can be used in water.
- Both do not require trailing wires.
- Both can detect the severity of the indication.
- Both can indicate if it is a single anomaly or a continuous anomaly.
- Both are affected by large indications overpowering nearby small indications.
- Both ACVG and DCVG can be less sensitive in high contact resistance areas (i.e. paved surfaces, very high resistant soils or rocky surfaces).

Differences from ACVG

- DCVG uses interrupted CP source or sources. ACVG uses either low frequency AC or interrupted DC (mimicking an AC signal).
- DCVG uses two poles with half cell type of contact probes. ACVG uses two metal probes.
- DCVG probe space varies. ACVG probe space is fixed.
- DCVG can be interfered with from existing or stray DC sources. ACVG normally is not.
- DCVG normally requires 400 – 500 mv shift which cannot be obtained in all pipeline conditions. ACVG requires a minimum amount of low frequency applied current.
- DCVG can be less sensitive under paved surfaces than ACVG.
- ACVG performs very well in high AC corridors.
- ACVG requires less operator interpretation because of the fixed spacing, unique applied signal and directional indication.
- Digital DCVG meters have a fixed directional indication like ACVG.
- DCVG can provide a relative cathodic/anodic condition of CP at an indication at that moment in time.

DCVG in-line technique

In carrying out a survey, the surveyor walks the pipeline route testing at regular intervals with the probes in a position of one in front of the other, separated by 3’ to 6’ above the pipeline. As a fault is approached, the surveyor will see the volt meter start to respond to the ON/OFF pulsed current, which is either a coating fault or interference from another structure. When the fault is passed, the needle deflection completely reverses and slowly decreases as the surveyor moves away from the fault. The surveyor then back up along the pipeline and where the needle or arrow indication reverses again, the fault is sited.

This procedure is repeated at right angles to the first set of observations and where the two midway positions cross is the epicenter of the voltage gradient. This is directly above the coating fault.

DCVG side by side technique

In carrying out a survey, the surveyor walks the pipeline route testing at regular intervals with the probes side by side to each other with one probe over the pipe and one off to the side 3’ to 6’. As a fault is approached, the surveyor will see the volt meter start to respond to the ON/OFF pulsed current and give a higher voltage measurement and or greater needle or arrow deflection. When the fault is passed, the voltage measurement decreases. The surveyor now moves the probes in-line with the pipe and continues in the same manner as an in-line survey. The surveyor then back up along the pipeline and where the needle or arrow indication reverses again, the fault is sited.

This procedure is repeated at right angles to the first set of observations and where the two midway positions cross is the epicenter of the voltage gradient. This is directly above the coating fault.

DCVG side drain and %IR

- Once an indication is found, the surveyor now must take a side drain measurement. This is completed by taking measurements over the pipe and at continuous distances to the side of the pipe until remote earth is reached. This total voltage value will be the total side drain voltage.
- This voltage is then used in conjunction with voltage measurements taken at pipe access points and the indication distance from those points to calculate a % IR. Digital meters can calculate this automatically while analogue meters will require manual calculation.
- DCVG indications are normally categorized as 1- 15% IR – very minor, 16% - 35% IR - minor, 36% - 60% IR – moderate, 61% - 100% IR - severe.

Problems/Solutions to DCVG surveys

- P - DC noise level too high for proper interpretation of field indications due to interfering DC sources. S - Add current with portable rectifiers to raise the amount of current change and voltage gradient near the indications.

- P - Fluctuating voltages due to interfering DC sources. S- Conduct survey at less interfering times (i.e. nighttime).

- P - Inability to find indications due to AC grounding for AC mitigation. S - Use filter(s) in CP system that discharges AC current but blocks DC current from earth where grounding is necessary for safety.
- P – Paved surfaces. S- wet down pavement or drill holes for lower contact resistance. May also have to raise the amount of current on the pipe.

DCVG graph results

DCVG Cathodic/Anodic results

36500	Custom 8	0	0	0	FLAG 730
36730	DCVG Anomaly: DCVG Max/Total	0.014264	0.014264	3.648994	
36730	DCVG Anomaly: DCVG Max On/Off	0.004001	-0.01026	0	Cathodic/Anodic
36755	DCVG Anomaly: DCVG Max/Total	0.024353	0.052707	13.48348	
36755	DCVG Anomaly: DCVG Max On/Off	0.018961	-0.00539	0	Cathodic/Anodic
37000	Custom 8	0	0	0	FLAG 740
37205	DCVG Anomaly: DCVG Max/Total	0.027136	0.085584	21.89396	
37205	DCVG Anomaly: DCVG Max On/Off	0.025049	-0.00209	0	Cathodic/Anodic
37500	Custom 8	0	0	0	FLAG 750
37540	DCVG Anomaly: DCVG Max/Total	0.011829	0.038965	9.967984	
37540	DCVG Anomaly: DCVG Max On/Off	0.039487	0.027658	0	Cathodic/Cathodic

What data is most important?

- IT DEPENDS!
  - What is the history of the line?
    - Leaks, Stray Current, TPI, dis-bondment, soils, CP, etc.
  - Are there shorts or bonds in the system?
  - Is there new coating followed by old coating?
  - Are there paved or very rocky areas?
  - How many rectifiers are in the system to be surveyed?
  - How many foreign crossings are there?
  - And the list goes on…

What data is most important? (cont.)

Multiple applicable tools are key to having a good ECDA indirect inspection survey.

While the rule only requires two inspection techniques it is almost always required at some locations to have a minimum of three.

Knowing where your holidays are AND the cathodic protection state are key in making informed decisions about External Corrosion.

Soils can also be of added value where the tools need supplemental data for support.

Of course any and all Pre-Assessment data is crucial to success.

Summary

- Combining data and tools are crucial to proper identification of possible external corrosion.
- Other items in the indirect inspections such as depth of cover and foreign crossings should be included in the analysis at indications to look for Third Party Damage.
- If one tool shows an indication and the others do not, it should be verified as to why this occurred and not ignored.
- Coating is not perfect. Therefore if you find nothing you need to find out why the tools didn't work, resolve the issues and resurvey where necessary.
- All local conditions must be considered before deciding what indications are monitored, scheduled and immediate.

Questions

- Jim Walton
- JW’s Corrosion Services, LLC
- Cell: 817-907-4444
- jim.walton@jwscorrosion.com